

# PRODUCT DESCRIPTION

Moland engineered wood flooring

Date: May 6<sup>th</sup>, 2021

Item number:	<b>13181261</b>
Product name:	<b>Loc Parket +, Oak UV-Lacquer, Matt</b>

## Picture



Picture no. 1

Picture no. 2

## Product description

Appearance	Parquet with natural yellowish to slight brown color (or oak wood in white color finishing), with brown and dark brown strips and clearly marked structure and characteristic for oak dark heartwood and knots. The oak floor characterizes with large changeability of tints. Up to 3% of the lamellas in a batch maybe from other classes.
Pattern of surface	3 strips
Finishing	5 layers of UV lacquer
Lacquer	UV lacquer, matt, gloss 9 - ±2
Oil	-
Hardness	Hard wood
Floor heating installation	Yes, max 27°

## Dimensions

Length	2200 mm	<input checked="" type="checkbox"/> Cleaning and maintenance instructions - <a href="http://www.moland.dk">www.moland.dk</a> <input type="checkbox"/> Can be used for eco-label construction. <input type="checkbox"/> FDV-documentation - <a href="http://www.moland.dk">www.moland.dk</a> <input checked="" type="checkbox"/> FSC <input type="checkbox"/> PEFC <input type="checkbox"/> No Label
Width	207 mm	
Thickness	14 mm	
Top layer	2.5 mm	
Split boards	- 7 x 2200 OR 6 x 2200 + 2 x 1092 OR 6 x 2200 + 1 x 2172 mm	

## Lamel sizes

-
---

# PRODUCT DESCRIPTION

Moland engineered wood flooring



Date: May 6<sup>th</sup>, 2021

## Technical specification

Dimension	14x207x2200 mm	Delamination	Not allowed
Top layer	2.5 mm ± 0.2 mm	Torn grain	Not allowed
Middle & bottom layer	11.5 mm	Colour on bevel and surface	Homogeneous expression
-	-	Pressure marks	Not allowed
Locking method end	M5	Product marking	CE
Locking method longside	M5	Boards per packet/ m <sup>2</sup>	7 boards = 3.18 m <sup>2</sup>
Fire class	Dfl- s1	Packet per pallet/ m <sup>2</sup>	40 packets = 127.2 m <sup>2</sup>
Formaldehyde content	E1		
Thermal conductivity	0.11 W/mk		

## Production tolerance

Moisture content	7% ±2%
Height difference	≤ 0.2 mm, 0.3 mm to a limited extent
Width	± 0.2 mm
Length	± 0.1%
Squareness	± 0.2% over the width
Crosswise bending	± 0.2% over the width
Longitudinal bending	± 1% of the length
Spring across the element	≤ 0.1% over the length

## Grading


Fresh knots	Acceptable, without limitations
Cracked filled knots	≤ 55 mm, filled with putty, partly filled cavities acceptable
Dead knots	≤ 25 mm, filled with putty, partly filled cavities acceptable
Dark lines	Allowed
Cracks	Acceptable up to 1 mm wide, up to 30mm length.
Bark pockets	Acceptable
Sapwood	Allowed
Structure variation	Allowed
Color variation	Allowed
Worm hole	Not allowed
Blue stained	Not allowed
Stain (discoloration)	Not allowed
Rot	Not allowed

# PRODUCT DESCRIPTION

Moland engineered wood flooring

Date: May 6<sup>th</sup>, 2021

## Packing



## Pallets

Number of boards per pack	7 boards
M <sup>2</sup> / pack	3.18 m <sup>2</sup>
Packs / pallet	40 packs
Layer / pallet	8 layers
M <sup>2</sup> / pallet	127.2 m <sup>2</sup>